



14700 Downey Avenue
P.O. Box 1418
Paramount, CA 90723-1418
(562) 531-2060

PRODUCT SPECIFICATIONS

PRODUCT: ASPHALT CEMENT

GRADE: AC-10 (Arizona) **PRODUCT CODE:** 13413

DESCRIPTION: A vacuum steam refined straight run asphalt for use in hot mixes in cooler temperature climates under normal load conditions.

MEETS SPECIFICATIONS: ASTM D3381, Table 1
AASHTO M226, Table 1

TESTS	ASTM METHOD	AASHTO METHOD	SPECS.	TYPICAL ANALYSIS ¹
Original Asphalt:				
Abs. Viscosity, 140°F, Poise	D2171	T202	800-1200	1071
Kin. Viscosity, 275°F, cSt	D2170	T201	150 min	235
Penetration, 77°F, 100g, 5s	D5	T49	70 min	92
Flash Point, P.M.C.C., °F	D93	T73	425 min	475
Solubility in TCE, wt. %	D2042	T44	99.0 min	99.9
Specific Gravity, 77/77 °F	D70	T228		1.018
Specific Gravity, 60/60 °F	D70	T228		1.024
API Gravity, 60°F	D70	T228		6.7
Density, 60°F, Lbs/Gallon	D70	T228		8.53
Residue from R.T.F.O. Test:				
Abs. Viscosity, 140°F, Poise	D2171	T202	4000 max	2381
Aging Index, 140°F	D2171	T202		2.2
Kin. Viscosity, 275°F, cSt	D2170	T201		340
Penetration, 77°F, 100g, 5s	D5	T49		54
% of Original Penetration	D5	T49		59
Penetration, 4°C, 200g, 60s	D5	T49		16
Ductility, 77°F, 5cm/min, cm	D113	T51	100 min	150+
Loss on Heating, wt. %	D2872	T240		0.6

¹Values shown as typicals may, at times, be superseded by results which are current at a particular time.

AVAILABILITY: Readily available

DOT SHIPPING NAME: UN3257, Elevated temperature liquid, n.o.s., 9, III

DOT PLACARD: Hot, 3257

RELEASED: 02-01-2003