



14700 Downey Avenue
P.O. Box 1418
Paramount, CA 90723-1418
(562) 531-2060

PRODUCT SPECIFICATIONS

PRODUCT: ASPHALT CEMENT

GRADE: AC-30 P

PRODUCT CODE: 13105

DESCRIPTION: A polymer modified vacuum steam refined straight run asphalt for use in hot mixes in moderate temperature climates under normal load conditions.

MEETS SPECIFICATIONS: Nevada DOT

TESTS	NEVADA METHOD	AASHTO METHOD	SPECS.	TYPICAL ANALYSIS ¹
Original Asphalt:				
Abs. Viscosity, 140°F, Poise	T727		3000 min	
Kin. Viscosity, 275°F, cSt		T201	600 - 3000	
Penetration, 77°F, 100g, 5s		T49		
Flash Point, C.O.C., °F		T48	450 min	
Ductility, 4°C, 5cm/min, cm	T746		20 min	
Toughness, inch-pounds	T745		150 min	
Tenacity, inch-pounds	T745		100 min	
Specific Gravity, 77/77 °F		T228		
Specific Gravity, 60/60 °F		T228		
API Gravity, 60°F		T228		
Density, 60°F, Lbs/Gallon		T228		
Residue from R.T.F.O. Test:				
Abs. Viscosity, 140°F, Poise	T727		6000 min	
Kin. Viscosity, 275°F, cSt		T201		
Penetration, 77°F, 100g, 5s		T49		
% of Original Penetration		T49		
Ductility, 4°C, 5cm/min, cm	T746		5 min	
Loss on Heating, wt.%		T240	1.0 max	

¹Values shown as typicals may, at times, be superseded by results which are current at a particular time.

AVAILABILITY: Special order only

DOT SHIPPING NAME: UN3257, Elevated temperature liquid, n.o.s., 9, III

DOT PLACARD: Hot, 3257

RELEASED: 02-01-2003