



14700 Downey Avenue
P.O. Box 1418
Paramount, CA 90723-1418
(562) 531-2060

PRODUCT SPECIFICATIONS

PRODUCT: Asphalt

GRADE: Modified Scrub Seal Base

PRODUCT CODE: 13153

DESCRIPTION:

MEETS SPECIFICATIONS: Paramount Petroleum

TESTS	ASTM METHOD	AASHTO METHOD	SPECS.	TYPICAL ANALYSIS*
Original Asphalt:				
Minimum Tire Rubber % (1)			10 min	
Abs. Viscosity, 140F, Poise	D2171	T202		
Kin. Viscosity, 275F, cSt	D2170	T201		
Penetration, 77F, 100g, 5s	D5	T49	0-40	10
Flash Point, C.O.C., F	D92	T48		
Softening Point °C	D36	T53	165 min	174
Solubility in TCE, wt %	D2042	T44		
Specific Gravity, 77/77F	D70	T228		
Specific Gravity, 60/60F	D70	T228	Report	1.0728
API Gravity, 60° Degrees F	D70	T228		
Elastic Recovery %	D6084			
Density, 60F, Lbs/Gallon	D70	T228		
Dynamic Shear @ 64°C, kPa		TP5		
Phase angle		TP5	2-5	3
Polymer content %	CAL401		1.0 min	1

*Values shown as typicals may, at times, be superseded by results, which are current at a particular time.

(1) tire rubber post added in the field

AVAILABILITY: Special Order Phoenix Facility

DOT SHIPPING NAME: UN3257, Elevated temperature liquid, n.o.s., 9, III

DOT PLACARD: Hot, 3257

RELEASED: 09/01/04