



14700 Downey Avenue  
P.O. Box 1418  
Paramount, CA 90723-1418  
(562) 531-2060

## PRODUCT SPECIFICATIONS

**PRODUCT:** ASPHALT CEMENT

**GRADE:** PBA-4

**PRODUCT CODE:** 13265

**DESCRIPTION:** A vacuum steam refined straight run asphalt for use in hot mixes in warmer temperature climates or under heavier load conditions.

**MEETS SPECIFICATIONS:** Caltrans

TESTS	ASTM METHOD	AASHTO METHOD	SPECS.	TYPICAL ANALYSIS <sup>1</sup>
Original Asphalt:				
Abs. Viscosity, 140°F, Poise	D2171	T202	2800 min	2981
Kin. Viscosity, 275°F, cSt	D2170	T201		394
Penetration, 77°F, 100g, 5s	D5	T49		39
Flash Point, C.O.C., °F	D92	T48	450 min	595
Solubility in TCE, wt. %	D2042	T44	99.0 min	99.9
Specific Gravity, 77/77 °F	D70	T228		1.020
Specific Gravity, 60/60 °F	D70	T228		1.026
API Gravity, 60°F	D70	T228		6.5
Density, 60°F, Lbs/Gallon	D70	T228		8.54
Residue from R.T.F.O. Test:				
Abs. Viscosity, 140°F, Poise	D2171	T202	14000 max	8108
Aging Index, 140°F	D2171	T202	4.0 max	2.7
Kin. Viscosity, 275°F, cSt	D2170	T201	350 min	545
Penetration, 77°F, 100g, 5s	D5	T49	20 min	21
% of Original Penetration	D5	T49		55
Penetration, 4°C, 200g, 60s	D5	T49		9
Ductility, 77°F, 5cm/min, cm	D113	T51	50 min	100+
Loss on Heating, wt.%	D2872	T240		0.2

<sup>1</sup>Values shown as typicals may, at times, be superseded by results which are current at a particular time.

**AVAILABILITY:** Readily available

**DOT SHIPPING NAME:** UN3257, Elevated temperature liquid, n.o.s., 9, III

**DOT PLACARD:** Hot, 3257

**RELEASED:** 02-01-2003